

SINO – JAPAN CHEMICAL CO., LTD.

Head office: 14 Fl. 99, Sec. 2, Jen Ai Rd., Taipei, Taiwan, R. O. C.
Factory: No. 6 Shih Hwa 4th Rd., Lin-Yuan. Kaohsiung Hsien, Taiwan.

Tel: (886) 2-23966223
Fax:(886) 2-23414628
Tel: (07) 6426311-5

SPECIFICATION

| | |
|---------------------------|------------------------------|
| ITEM | SINOPOL 1105H |
| COMPOSITION | Polyoxyethylene Lauryl Ether |
| APPEARANCE(30°C) | Liquid |
| COLOR | A-80 Max |
| PH (1%aq) | 5-7 |
| MOISTURE (%) | 0.5 Max |
| SPECIFIC GRAVITY(30°C) | 0.935-0.955 |
| Hydroxyl Value (mg KOH/g) | 138-145 |
| HLB | 9.4 |
| PACKING | 190Kg / Iron drum |